



Preliminary Technical Data Sheet

### ExpandoThane™

ExpandoThane™ comprises a microcellular elastomeric spray polyurethane/polyurea hybrid system. This system may be applied by both low-pressure, air assisted machines or high pressure, plural component machines at volume ratio of 1:1.

#### Description

#### Preliminary Component Properties

	Units	ExpandoThane Polyol	ExpandoThane Isocyanate	Test Method
Appearance		Black liquid	Pale yellow liquid	Visual
Density (23°C)	g/cm <sup>3</sup>	1.01	1.12	ASTM D1475
Viscosity (23°C)	cP	600 – 900	500-1000	ASTM D4287
Flash Point	°C	>100	>150	Closed Cup

These are typical values and should not be construed as specifications.

#### Recommended Process Conditions

The Polyol component must be mixed until homogenous before use. The material is processed with a two component high pressure dosing machine using impingement mixing technology, a feed rate of 0.5 to 2 gallons/minute, and a round nozzle.

	Unit	Value
ExpandoThane Polyol	Vol.	1.00
ExpandoThane Isocyanate	Vol.	1.00
Typical component temperature (both components, tanks and hose the same).	°F	140-150
Typical component pressures	psi	1,500-2,000

#### Typical Reaction Characteristics\*

	Unit	Value
Gel time	s	10
Tack-free time	s	16

\* - Values refer to test made with a two-component, high pressure machine run according to the recommended process conditions above; Typical values and should not be construed as specifications.

## Handling and Storage

	Units	ExpandoThane Polyol	ExpandoThane Isocyanate
Storage temperature	°C	15-25	15-25
Storage stability / Shelf life <sup>(1)</sup>	months	12	6

1. Both polyol and isocyanate components must be protected against humidity and stored in sealed containers.

## Typical Polymer Properties

	Unit	Value	Test Method
Hardness	Shore A	62	ASTM D2240
Tensile strength	psi	360	ASTM D412
Elongation at break	%	100	ASTM D412
Tear resistance	pli	59	ASTM D624C
Density	lb/ft <sup>3</sup>	27-29	DIN 53479

These are typical values and should not be construed as specifications

## Precautions

The use of this two-component system required special precautions. Please refer to the material safety data (MSD) sheet before using. Avoid inhalation of the vapour and contact with skin and eyes. Working areas should be well ventilated with fresh air.

Use protective gloves and goggles. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. In case of contact with skin, wash immediately with plenty of water and soap. During spray application, wear suitable respiratory equipment.

## Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Safety Considerations

Material Safety Data (MSD) sheets are available from The Dow Chemical Company. MSD sheets are provided to help customers satisfy their own handling, safety and disposal needs and those that may be required by locally applicable health and safety regulations. MSD sheets are updated regularly, therefore, please request and review the most current MSD sheet before handling or using any product. These are available from the nearest Dow sales office.

## Customer Notice

Dow encourages its customers to review their application of Dow products from the standpoint of human health and environmental quality. To help ensure that Dow products are not used in ways for which they were not intended or tested, Dow personnel will assist customers in dealing with ecological and products safety. Your Dow sales representative can arrange the proper contacts.

### Contact information:

For more information about this product please call  
The Dow Chemical Company.

North America: 1-800-447-4369  
Latin America: (+55) 11-5184-8722  
Europe: (+31) 11-567-2626  
Asia/Pacific: (+60) 3-7965-5392  
<http://www.dow.com/polyurethane>

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED

