



American Spray Foam
850709 US Highway 17 Yulee, FL 32097
877-772-9629
www.AmericanSprayFoam.com

TECHNICAL DATA SHEET

ASF 2.0 SPRAY FOAM SYSTEM

DESCRIPTION:

ASF 2.0 is a two component, self-adhering, seamless, closed cell, spray applied polyurethane foam system. This AMERICAN SPRAY FOAM system has been formulated with highly insulating HFC-245fa as the blowing agent. The ASF 2.0 insulation system is suitable for application on the exterior or interior side of Type I, II, III, IV, & V buildings as well as other insulation applications. It complies with AC 377 and ASTM C1029. ASF 2.0 is certified for application in ABAA projects.

DISTINGUISHING CHARACTERISTICS:

- High R-Value
- Zero ODP
- Moisture Vapor Retarder - Class II @ 1.3"
High Yields Approved with DC315 coating in lieu of code prescribed Thermal Barrier
- Air Barrier, ABAA Certified @1"
- Good Dimensional Stability
- Meets ASTM E-84, FS <25, SD <450 @ 4"
- FEMA Flood Resistance - Class 5
- Water Resistive Barrier (AC71) @1"
- Passed NFPA 285
- Approved in multiple UL
Fire Resistive Assemblies
- Low VOC per CDPH Standard V 1.2, 2017

For proper use of this AMERICAN SPRAY FOAM insulating material refer to the AMERICAN SPRAY FOAM Application Information and any of the following codes or guides:

- 2018 International Building Code Chapter 26
- 2018 International Residential Code
- Section R316 and R806
- ICC-ES Evaluation Report 1615
- API Fire Safety Guidelines for Use of Rigid Polyurethane and Polyisocyanurate Foam Insulation in Building Construction (AX230)

TYPICAL PHYSICAL PROPERTIES*1:

Free Rise Core Density*2 ASTM D 1622	2.0 pcf
Compressive Strength ASTM D 1621	27 psi
Moisture Vapor Transmission - ASTM E 96	1.3 perm-in
Closed Cell Content ASTM D 6226	>90%
R-value @ 1" - ASTM C 518	6.8
Air Permeance @1" Infiltration ASTM E 283 & 2178 Exfiltration	0.000 cfm/ft ² @ 1.57 psf 0.000 cfm/ft ² @ 1.57 psf
Bacterial & Fungal Growth ASTM G 21 & E 1428	Negligible*3
STC - ASTM E 90 OITC - ASTM E 90	31*4 24*4
Flammability ASTM E-84 @ 4 inches	Flame Spread :525 Smoke Dev :5450
Potential Heat—NFPA 259	1989 Btu/ft ² /inch
Max Service Temperature	180°F

*1The above values are average values obtained from laboratory experiments and should serve only as guide lines.

*2Free rise core density should not be confused with overall density. Overall densities are always higher than free rise core densities and take into account skin formation, thickness of application, environmental conditions, etc.

*3See page 4 for details.

*4As measured in a 2" x 4" studwall assembly.

Polyurethane products manufactured or produced from this liquid system may present a serious fire hazard if improperly used or allowed to remain exposed or unprotected. The character and magnitude of any such hazard will depend on a broad range of factors, which are controlled and influenced by the manufacturing and production process, by the mode of application or installation and by the function and usage of the particular product. **Any flammability rating contained in this literature is not intended to reflect hazards presented by this or any other material under actual fire conditions. These ratings are used solely to measure and describe the product's response to heat and flame under controlled laboratory conditions.** Each person, firm or corporation engaged in the manufacture, production, application, installation or use of any polyurethane product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures.



ASF 2.0 Insulation

R-Values*				
Thickness (inches)	R-Value (°F-hr-ft² / Btu)	Moisture Vapor Perm	Installation Limitations with a prescriptive Thermal Barrier	Limitations with DC 315 Coating on the foam in lieu of a Thermal Barrier
1	6.8	1.3	No limit for Thickness in walls	In vertical wall max thickness 5.5" with DC 315 applied at 14 wet mils (9 dry mils)
2	13	0.65		
3	20	0.43		
3.5	23	0.37		
4.75	30	0.27	No limit for Thickness in ceilings/roof decks	Underside of roof decks max thickness 9.5" with DC 315 applied at 14 wet mils (9 dry mils)
5.5	35	0.24		
6	38	0.22		
9.5	61	0.14		
10	64	0.13		
*Note: As with all insulating materials, the R-value will vary with age and use conditions.				

Property	Test Method	Test Condition	Result	<p>Approved for Wind-Uplift resistance when installed under the roof deck at rafter/truss connection.</p> <p>Florida Product Approval #9975 with plywood decks are rated to 190 psf and OSB decks are rated to 2.0 psf.</p> <p>Miami-Dade NOA with plywood decks rated to 142.5 psf.</p> <p>ASF 2.0 provides the Secondary Water Resistive Barrier</p>
Air Barrier Certification	ASTM E 283	Infiltration @ 1.57 psf	1 inch thickness 0.0000 cfm/ft ²	
	ASTM E 2178	Exfiltration @ 1.57 psf	1 inch thickness 0.0000 cfm/ft ²	
Water Resistance	AATCC 127-1998	@ 56.5 ft	1 inch thickness No failure	
	ASTM E 331	6.24 psf	1 inch thickness No Penetration	

ASF 2.0 closed cell spray foam system is an approved Air Barrier material per the Air Barrier Association of America (ABAA) and is certified per AC 71 as a Water Resistive Material when installed on the exterior side of walls. Exterior wall coverings of this spray foam system may be restricted. Contact AMERICAN SPRAY FOAM for the current approvals.





ASF 2.0 Application Information

STORAGE AND USE OF CHEMICALS:

The ASF 2.0 chemicals consisting of the A2-000 and B11-016 drums should be between 65°F and 80°F for proper processing through the spray equipment. Chemicals shipped during winter or summer months may need extra time in moderate temperature storage to stabilize back in the proper application range. Cold chemicals can cause poor mixing, pump cavitation or other process problems due to higher viscosity at lower temperatures.

Storing chemicals above 90°F should be avoided as much as possible. Excessively warm chemicals should be cooled prior to opening the drums. Do not store in direct sunlight. Keep drums tightly closed when not in use and under dry air or nitrogen pressure of 2-3 psi after they have been opened. When properly stored, unopened drums of A2-000 have a shelf life of 24 months and B11-016 drums have a shelf life of 6 months.

SAFE HANDLING OF LIQUID COMPONENTS:

Use caution in removing bungs from the container. Loosen the small bung first to allow any built-up vapor pressure to stabilize before completely removing. **B component will froth at elevated temperatures.** Avoid prolonged breathing of vapors. In case of chemical contact with eyes, flush with water for at least 15 minutes and get medical attention. For further information refer to www.spraypolyurethane.org, Resources box, "Health and Safety Product Stewardship Workbook for High-Pressure Application of SPF".

APPLICATION GUIDELINES:

ASF 2.0 is suitable for application to most construction materials including wood, masonry, concrete, and metal. Application can be to the exterior or interior side of wall surfaces. ASF 2.0 can be applied to surfaces that will be in contact with soil and intermittent contact with water, such as below grade exterior foundation and basement walls or under concrete slab floors. To ensure proper adhesion, all substrate surfaces should be dry, clean of dust or flaking surface rust, ice or frost. All metal surfaces must be free of oil, grease, etc. Uncoated metals may require a primer coat.

No flammable chemicals, such as wasp and hornet sprays, should be sprayed in the area of the foam application 24 hours before the application. No such chemical can be sprayed after the foam application until the foam has cooled to room temperature.

APPLICATION AROUND PLASTIC PIPES:

Based on a series of extensive studies, the ASF 2.0 system can be applied in contact with PVC, CPVC, ABS, PP-R and PEX plastic pipes.

The pipes must not be pressurized during the foam application. The foam pass applied in contact with the pipe should not exceed 2" thick in order to prevent excessive exothermic heat at the pipe to foam interface. Allow a 2 minute cooling between each additional foam pass. The total foam thickness is limited to that thickness permitted in that area of the building assembly.

APPLICATION AROUND ELECTRICAL WIRES:

Based on AMERICAN SPRAY FOAM testing, the ASF 2.0 system can be applied in contact with electrical wires.

Spray foam applicators must spray the foam in such a manner that the expanding foam does not stretch and distort the wires. Light gauge wires which will be encapsulated in the foam layer should have the foam installed behind the wires and allowed to cool prior to applying a top layer to cover the wire. Use a shallow lift of 3/4" of foam to cover the wire. Wait the required 2 minutes between passes when adding more foam thickness to achieve the desired R-value.

APPLICATION PASS THICKNESS:

Spraying foam will generate heat. Foam which is applied too thick in single passes can build temperatures which will degrade cell structure and not produce foam with optimum properties. In the most extreme case, ASF 2.0 could reach dangerously high temperatures inside the finished foam which could lead to splitting, charring, or even spontaneous combustion. The maximum pass thickness for ASF 2.0 is 4 inches. When applying pass thicknesses greater than 2 inches, wait 10 minutes or until the foam surface has cooled to ambient temperature before adding additional foam passes. Multiple layers can be applied to achieve the desired R-value..

VENTILATION OF SPRAY AREA:

Spraying foam will generate a mist and airborne particulates. For interior applications the building area must be vented with fresh air to dissipate the particulates. The amount of air flow and time for venting will vary based on each situation. Details regarding ventilation is provided in the Spray Foam Coalition document "Ventilation Considerations for Spray Polyurethane Foam" found in the AMERICAN SPRAY FOAM Product Stewardship Manual (PSM). SPF Contractors should refer to this guidance prior to beginning any spray foam application project. Reentry time and reoccupancy time is provided in the AMERICAN SPRAY FOAM Technical Bulletin - Ventilation Requirements for Reentry of Spaces After Spraying Closed Cell Spray Foams.

ASF 2.0 Application Information

EQUIPMENT AND COMPONENT RATIOS:

ASF 2.0 should be sprayed with plural component proportioning pump designed for polyurethane spray foam. The B-11-016 drum is connected to the resin pumps with the A2-000 drum connected to the isocyanate pumps. The proportioning pump ratio is 1 to 1 by volume.

The preheater and hose temperature should be set at 130°F to give a good pattern. Due to equipment variations, the application temperature settings may be adjusted to achieve a good spray pattern. For higher-pressure settings above 1,000 psi, temperature settings can be slightly lower.

OPTIMUM ADHESION TEMPERATURE OF SURFACE TO BE SPRAYED:

The surface should be between 10°F and 120°F. In this range the warmer the surface, the better the adhesion. AMERICAN SPRAY FOAM has three grades of ASF 2.0 foam for this application range: G-series designed for temperatures no lower than 50°F, M-series designed for temperatures as low as 20°F and the X-series, when processing must be conducted down to temperatures as low as 10°F. For best results, when surfaces to be sprayed are cooler than 60°F, a flash coat should be applied with the second coat following as soon as the original coat is no longer tacky to the touch.

BACTERIA AND FUNGUS RESISTANCE:

ASF 2.0 is naturally able to inhibit the growth of bacteria and fungus (mold) per the ASTM G-21 and E-1428 tests. The anti-microbial properties do not protect occupants of spaces insulated with ASF 2.0 from potential deleterious effects of molds, mold spores, or disease organisms that may be present in the environment.

VAPOR BARRIER PROTECTION ON COLD STORAGE APPLICATIONS:

When ASF 2.0 is used in structures subject to continuous cold temperatures, such as coolers and freezers, a Class I moisture vapor barrier (0.1 perm or less) is normally required on the "warm" side of the foam insulation. Contact AMERICAN SPRAY FOAM for specific recommendations.

WEATHER PROTECTION OF FINISHED FOAM ON EXTERIOR APPLICATIONS:

The finished surface of sprayed polyurethane foam should be protected from adverse effects of ultraviolet rays of direct sunlight which can cause dusting and discoloration. Protective coatings designed for use with polyurethane foam are available. On exterior applications where a masonry veneer or mechanically attached covering is to be installed, the ASF 2.0 foam surface may be exposed to UV light up to 6 months.

CODE-COMPLIANT FIRE RESISTANCE:

Building Codes require foam plastic insulation, such as, be separated from the interior of the building by a 15 minute thermal barrier of ½" gypsum board or other approved material. Refer to specific building codes for details.

11-016 has passed testing with the DC315 intumescent coating in lieu of the thermal barrier. When covering the foam with DC315, the foam thickness on walls is limited to a maximum of 5.5" and on roof/ceiling assemblies the maximum thickness is 9.5". The DC315 is applied at 14 mills wet film thickness, or 1 gallon per 115 square feet.

OTHER APPLICATION AND SAFETY CONSIDERATIONS:

Before ASF 2.0 is to be applied, there are many safety and application situations to consider. All spray foam applicators must evaluate the job prior to beginning the spray foam application. It is impossible to anticipate every issue and provide explicit guidance in this product data sheet. If there is a question regarding some aspect of the planned application, consult with AMERICAN SPRAY FOAM for more guidance. The AMERICAN SPRAY FOAM Product Stewardship Manual contains additional information and should be reviewed often enough by all spray foam applicators to remain familiar with the contents. The American Chemistry Council (ACC), the Center for Polyurethanes Industry (CPI) and the Spray Polyurethane Foam Alliance (SPFA) also publish information regarding the safe handling and application of spray foam chemicals.

If there are any questions regarding the application of the ASF 2.0 system, contact an AMERICAN SPRAY FOAM representative.

The information on our data sheets is to assist customers in determining whether our products are suitable for their applications. The customers must satisfy themselves as to the suitability for specific cases. AMERICAN SPRAY FOAM warrants only that the material shall meet its specifications. This warranty is in lieu of all other written or unwritten, expressed or implied warranties, and AMERICAN SPRAY FOAM expressly disclaims any warranty of merchantability, fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the material. Failure to adhere to any recommended procedures shall relieve AMERICAN SPRAY FOAM of all liability with respect to the material or the use thereof.

AMERICAN SPRAY FOAM 8229 877-772-9629 www.AMERICANSPRAYFOAM.com

